



**INSTITUTO DE CIENCIAS  
DE LA CONSTRUCCIÓN  
EDUARDO TORROJA**

*C/ Serrano Galvache n. 4. 28033 Madrid (Spain)  
Tel.: (34) 91 302 04 40 / Fax: (34) 91 302 07 00  
[direccion.ietcc@csic.es](mailto:direccion.ietcc@csic.es) [www.ietcc.csic.es](http://www.ietcc.csic.es)*



## European Technical Assessment

**ETA 10/ 0342**  
**1/ 11/ 2015**

English translation prepared by IETcc. Original version in Spanish language

### General Part

**Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) Nº305/2011:**

Instituto de Ciencias de la Construcción Eduardo Torroja (IETcc)

**Trade name of the construction product**

**ALP ELAST**

**Product family to which the construction product belongs**

Liquid Applied Roof Waterproofing Kit, based on Water Dispersible polymers

**Manufacturer**

**CROMOLOGY S.L.**  
C/ Francia, 7 - Pol. Ind. Pla de Llerona  
08520 - Les Franqueses del Vallès. Barcelona.  
Spain.

**Manufacturing plant(s)**

C/ Francia, 7 - Pol. Ind. Pla de Llerona  
08520 - Les Franqueses del Vallès. Barcelona.  
Spain.

**This European Technical Assessment contains**

7 pages including 1 Annexes which form an integral part of this assessment.  
Annex 2. Contain confidential information and is not included in the ETA when that assessment is publicly available

**This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of**

Guideline for European Technical Approval (ETAG) nº 005, part 1-8 ed. 2004, used as European Assessment Document (EAD)

**This version replaces**

ETA 10/ 0343 issued on 10/ 08/ 2010

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission according to Article 25 Paragraph 3 of Regulation (EU) No 305/2011.

## SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

### 1 Technical description of the product

The Liquid Applied Roof Waterproofing Kit (LARWK) "ALP ELAST" is designed and installed in accordance with the manufacturer, design and installation instructions, deposited at the IETcc. This LARWK comprises the following components:

Components	Trade name	Consume
Waterproofing membrane	ALP ELAST	$\geq 2,5 \text{ kg/m}^2$ .
Internal reinforcement	TEXNON 300	$\geq 280 \text{ g/m}^2$

ALP ELAST is a one component liquid applied roof waterproofing based on water dispersible polymers, consists of a water dispersible styrene - acrylic copolymers, elastomeric with an internal reinforcing mesh; which once polymerized conforms an elastic lining, in form of a layer completely bonded to the support (steel, concrete, mortar, ceramic). The minimum layer thickness of the assembled membrane has to be 1,5 mm.

### 2 Specification of the intended use in accordance with the applicable EAD

The intended use of this System is the waterproofing of roof against the water, as in liquid as vapour form. This LARWK fulfils the Essential Requirements nº 2 (Safety in case of fire), nº 3 (Hygiene, health and the environment) and nº 4 (Safety in use) of the European Regulation 305/11.

This LARWK is made of non load-bearing construction elements. It does not contribute directly to the stability of the roof on which is installed, but it can contribute its durability by providing enhanced protection from the effect of weathering.

This LARWK can be used on new or existing (retrofit) roofs. It can also be used on vertical surfaces (singular details).

The performance levels of this System according to the Guide ETAG 005 Part. 1 and 8 are included in the annex 1. The provisions made in this European Technical Approval (ETA) are based on an assumed intended working life of the system of 10 years (W2). The indication given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are only to be regarded as a means for choosing the right products in relation to the expected economically reasonable working life of the works. "Assumed intended working life" means that, when an assessment following the ETAG provisions is made, and when this working life has elapsed, the real working life may be, in normal use conditions, considerably longer without major degradation affecting the Essential Requirements.

**Installation.** The Kit is installed on site. It is the responsibility of the manufacturer to guarantee that the information about design and installation of this system is effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this ETA. Besides, all the data concerning the execution shall be clearly indicated on the packaging and/or the enclosed instruction sheets using one or several illustrations.

**Design.** The fitness of the respective use for the levels of performance of this System stated in Annex 1 complies with the Spanish national requirements. In the MTD the manufacture gives information on the quantities consumed and the processing, which shall lead to a thickness of the roof waterproofing  $\geq 1.5 \text{ mm}$ .

**Execution.** Particularly, it is recommended to consider the:

- kit installation has to be carried out by qualified installers and it can only be used the components of the kit indicated in this ETA,
- supervision of the amount of material used ( $\text{kg/m}^2$ ) and the control visual to check that each coat cover totally the one below, can ensure the minimum thickness of the kits, inspection of the roof surface (cleanliness and correct preparation) before applying the roof waterproofing,
- recommended temperature of the product to be assembled will be between  $5^\circ\text{C}$  and  $40^\circ\text{C}$  and it will be not admitted support temperatures upper to  $45^\circ\text{C}$ . In other conditions it will need to follow the manufacturer's instructions.

Before, the installation of ALP ELAST, it is recommended to read its security card.

**Use, maintenance and repair of the works.** In those roofs with deteriorated areas of the waterproof layers, they will be repaired removing all the deteriorated layers. Afterwards, the new product will be assembled following the installation instruction and the new coats must overlap, at least 15-20 cm, to the coat no deteriorated. Further installation details are laid down in the MTD place at IETcc.

### 3 Performance of the product and references to the methods used for its assessment

The identification tests and the assessment for the intended use of this LARWK according to the Essential Requirements were carried out in compliance with the ETA Guidance n° 005: Guideline for European Technical Approval of Liquid applied roof waterproofing kits, ETAG 005, edition 2004/2000, Part 1"General" and Part 8 "Specific stipulations for kits based on water dispersible polymers" (called ETAG 005, in this ETA).

#### 3.1 LARWK Characteristics

##### Safety in case of fire ((BWR 2)

**External fire performance.** Classification: B<sub>roof</sub>(t1) according EN 13501-5 for supports with fire classification A1-A2, and roof slope <20°.

**Reaction to fire.** Euroclass F

##### Hygiene, health and environment (BWR 3)

**Resistance to water vapour** (EN 1931).  $\mu = 1100$

**Watertightness** (EOTA TR-003). Watertight

**Statement of dangerous substances.** According to the manufacturer's declaration taking account of EOTA TR 034, the product installed does not contain and release any dangerous substance.

**Resistance to wind loads** (EOTA TR-4). Pass (>50 kPa)

**Resistance to dynamic indentation** (EOTA TR- 6). Resistance Level: I4

**Resistance to static indentation** (EOTA TR-7). Resistance Level: L3

**Resistance to fatigue movement** (500 cycles) (EOTA TR-8). Pass

**Resistance to low temperatures effects (-20°C).** Dynamic indentation, Resistance Level I4

**Resistance to high temperatures effects.** Static indentation

Temperature °C	Support	Load (N)	Resistance level
60°	Steel	150	L2
90°	Steel	70	L1

**Resistance to heat ageing** (EOTA TR-11). The samples are exposed to 70°C during 200 days.

Properties	Values
Fatigue movement	Pass
Dynamic indentation (-20°C) (steel )	I4
Tensile strength (MPa) (EN ISO 527-3) ( <i>without reinforcement / reinforcement</i> )	4 / 24
Tensile elongation (%) (EN ISO 527-3) ( <i>without reinforcement / reinforcement</i> )	111 / 2

**Resistance to UV-radiation in the presence of moisture** (EOTA TR- 10). The samples are exposed 2000 hours to UV-radiation.

Properties	Values
Dynamic indentation (-10°C) (steel / PU)	I4
Tensile strength (MPa) (Type 2) (EN ISO 527-3) ( <i>without reinforcement / reinforcement</i> )	4 / 13
Tensile elongation (%) (EN ISO 527-3) ( <i>without reinforcement / reinforcement</i> )	80 / 2

**Resistance to hot water ageing** (EOTA TR-12). The samples are kept in touch with water at 60°C over 30 days.

Properties	Values
Delamination strength (kPa) (Concrete)	1000
Static indentation (60°C)	L1
Static indentation (90°C)	L1

Resistance to wind loads Pass (>50 kPa)

**Resistance to plant roots** (EN 13948). NPD

Safety in use (BWR 4)

**Slipperiness** (EN 13893). NPD.

Related aspects of serviceability

**Effect of weather conditions.** The system does show changes in its tensile properties and dynamic indentation, when the system is assembled and cured under two temperature conditions of 5°C and 40°C, and these values obtained complied with the manufacturer's specifications (pass).

**Effect of day joints.** The delamination strength test performed on a layer assembled over other one, it does not show an delamination strength decrease upper 20% of the value obtained in the layer assembled over the concrete support (pass).

### 3.2 Characteristics of the components

The characteristics of the components of this System show the following values, which compliance with their respective tolerances stated in the Manufacture Technical Dossier (MTD).

**ALP ELAST.** Waterproofing liquid constituted by a water dispersible styrene - acrylic copolymers, with loads and pigments mineral, and additives (anti-air entering, biocides, etc.). The main characteristics of this waterproof liquid are:

Properties	ALP ELAST
Density (g/cm <sup>3</sup> ) (ISO 1675)	1,25 -1,35
Dry extract (105°C) (% weight) (EN 1768)	60 – 65
Ash content (450°C) (% weight) (EN 1879)	30-35

**TEXNON 300.** Internal layer by glass fibre used as reinforcement of the membrane

Properties	TEXNON 300
Mass per unit area (g/m <sup>2</sup> ) (EN 29073-1)	280-320
Tensile elongation (%) (EN 29073-3)	3,8
Tensile strength (N/5cm) (EN 29073-2)	< 0,5

## 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

**System of Attestation of Conformity.** The European Commission according to her decision (98/599/EC of October 1998, Official Journal of the European Communities N° L 287, 24.10.1998) on the procedure of attestation of conformity for the procedure of attestation of conformity (Annex III, clause 2(ii) second possibility of EU Regulation 305/2011) for liquid applied roof waterproofing kits has laid down for this Kits.

Product	Intended uses	Level or Classes	System
ALP ELAST	Liquid Applied Roof Waterproofing Kit	Any	3

According to this decision, system 3 of Attestation of Conformity also applies with regard to external fire performance. The system 3 provides: Tasks for the manufacturer: Factory production control and Tasks for the approved body: Initial type-testing of the product.

## 5 Technical details necessary for the implementation of the AVCP system, as provided for the applicable EAD

The ETA is issued for this kit on the basis of agreed data/information, deposited at IETcc, which identifies the product that has been assessed and judged. It is the manufacturer's responsibility to make sure that all those who use the kit are appropriately informed of specific conditions according to sections 1, 2, 4 and 5 including the annexes of this ETA. Changes to the ETICS or the components or their production process, which could result in this deposited data/information being incorrect should be notified to the IETcc before the changes are introduced. IETcc will decide whether or not such changes affect the ETA and if so whether further assessment or alterations to the ETA shall be necessary.

### 5.1 Tasks of the manufacturer

**Factory production control.** The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this ETA.

The manufacturer may only use components stated in the technical documentation of this ETA including Control Plan. The incoming raw materials are subjected to verifications by the manufacturer before acceptance.

The factory production control shall be in accordance with the Control Plan<sup>(1)</sup> which is part of the Technical Documentation of this ETA. The Control Plan has been agreed between the manufacturer and the IETcc and is laid down in the context of the factory production control system operated by the manufacturer and deposited at the IETcc. The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan

**Other tasks of the manufacturer.** The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in section 4 in the field of LARWK in order to undertake the actions laid down in this clause. For this purpose, the control plan shall be handed over by the manufacturer to the notified bodies involved.

For initial type – testing, the results of the tests performed as part of the assessment for the ETA shall be used unless there are changes in the production line or plant. In such cases the necessary initial type- testing has to be agreed with the IETcc.

The manufacturer shall make a declaration of conformity, stating that the construction product is in conformity with the provisions of this ETA.

### 5.2 Tasks of notified bodies. The notified body shall perform

**Initial type-testing of the product.** The initial type-testing have been conducted by the IETcc to issued this ETA in accordance with chapter 5 of the guideline “Liquid applied roof waterproofing kits” (ETAG 005) part 1 and 8. The verifications underlying this ETA have been furnished on samples from the current production; these will replace the initial type-testing carried out by the manufacturer. The IETcc has assessed the results of these tests in accordance with chapter 6 of this ETA –Guideline, as part of the ETA issuing procedure.

---

<sup>(1)</sup> The control plan is a confidential part of this European Technical Assessment and only handed over to the notified body involved in the procedure of attestation of conformity. See section 3.2.2.

Issued in Madrid on 1 November 2015.  
by



Instituto de Ciencias de la Construcción Eduardo Torroja  
**CONSEJO SUPERIOR DE INVESTIGACIONES CIENTÍFICAS**  
c/ Serrano Galvache 4. 28033 Madrid (Spain).  
director.ietcc@csic.es www.ietcc.csic.es



On behalf of the Instituto de Ciencias de la Construcción Eduardo Torroja

Marta M<sup>o</sup> Castellote Armero  
Director

## Annex 1.

### Characteristics of the System "ALP ELAST"

Minimum thickness	1,5 mm
Water vapour diffusion resistant factor	$\mu \approx 1100$
Resistance to wind loads	> 50 kPa
Resistance to plant roots	NPD
Statement on dangerous substances	Does not contain any
Resistance to slipperiness	NPD

### Performance levels according to the intended use

External fire performance	Broof (t1) roof slope < 20° and support A1-A2
Fire reaction	F
Expected working life	W2
Climatic zone of use	S (Severe)
User loads	P1
Roofs slopes	S1 – S4
Minimum surface temperatures	TL3 (- 20 °C)
Maximum surface temperatures	TH4 (90°C)