



**INSTITUTO DE CIENCIAS
DE LA CONSTRUCCIÓN
EDUARDO TORROJA**

*C/ Serrano Galvache n. 4. 28033 Madrid (Spain)
Tel.: (34) 91 302 04 40 / Fax: (34) 91 302 07 00
direccion.ietcc@csic.es www.ietcc.csic.es*



European Technical Assessment

**ETA 15/ 0111
of 24/ 02/ 2015**

English translation prepared by IETcc. Original version in Spanish language

General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) N°305/2011:

Instituto de Ciencias de la Construcción Eduardo Torroja (IETcc)

Trade name of the construction product

MAXELASTIC POLY

Product family to which the construction product belongs

Liquid Applied Roof Waterproofing Kit, based on pure Polyurea

Manufacturer

DRIZORO S.A.U.
c/ Primavera 50-52, P.I. Las Monjas
28850 Torrejón de Ardoz (MADRID)

Manufacturing plant(s)

Plant 1.

This European Technical Assessment contains

8 pages including 1 Annex which form an integral part of this assessment.
Annex 2. Contain confidential information and is not included in the ETA when that assessment is publicly available

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of

Guideline for European Technical Approval (ETAG) nº 005, part 1-6 ed. 2004, used as European Assessment Document (EAD)

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission according to Article 25 Paragraph 3 of Regulation (EU) No 305/2011.

SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of the product

The Liquid Applied Roof Waterproofing Kit (LARWK) "MAXELASTIC POLY" is designed and installed in accordance with the manufacturer, design and installation instructions, deposited at the IETcc⁽¹⁾. This LARWK comprises the following components, which are factory produced by the manufacturer or a supplier.

Componentes	Trade name	Consume
Primer	MAXURETHANE PRIMER	≥ 0.2 kg/m ²
Waterproofing membrane	MAXELASTIC POLY	≥1.5 kg/m ² .
Finish layer: Protection UV	MAXURETHANE 2C	≥ 250 g/m ²
Coat Slipperiness	BISEAL MEV	8 % weight mixed with MAXURETHANE 2C

MAXELASTIC POLY is a liquid applied roof waterproofing based on pure polyurea 100%, consists of a pure polyurea resins, bi-component, elastomeric without internal protection layer; which once polymerised conforms an elastic lining, in form of a layer completely bonded to the support (steel, concrete, mortar, ceramic, extruded polystyrene). The minimum layer thickness of the assembled membrane has to be 1,4 mm.

2 Specification of the intended use in accordance with the applicable EAD

The intended use of this System is the waterproofing of roof against the water, as in liquid as vapour form. This LARWK fulfils the Essential Requirements nº 2 (Safety in case of fire), nº 3 (Hygiene, health and the environment) and nº 4 (Safety in use) of the European Regulation 305/11.

This LARWK is made of non load-bearing construction elements. It does not contribute directly to the stability of the roof on which is installed, but it can contribute its durability by providing enhanced protection from the effect of weathering.

This LARWK can be used on new or existing (retrofit) roofs. It can also be used on vertical surfaces (singular details).

The performance levels of this System according to the Guide ETAG 005 Part. 1 and 6 are included in the annex 1. The provisions made in this European Technical Approval (ETA) are based on an assumed intended working life of the system of 25 years (W3). The indication given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are only to be regarded as a means for choosing the right products in relation to the expected economically reasonable working life of the works. "Assumed intended working life" means that, when an assessment following the ETAG provisions is made, and when this working life has elapsed, the real working life may be, in normal use conditions, considerably longer without major degradation affecting the Essential Requirements.

Installation. The Kit is installed on site. It is the responsibility of the manufacturer to guarantee that the information about design and installation of this system is effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this ETA. Besides, all the data concerning the execution shall be clearly indicated on the packaging and/or the enclosed instruction sheets using one or several illustrations.

Design. The fitness of the respective use for the levels of performance of this System stated in Annex 1 complies with the Spanish national requirements. In the MTD the manufacture gives information on the quantities consumed and the processing, which shall lead to a thickness of the roof waterproofing ≥1.4 mm.

Execution. Particularly, it is recommended to consider:

- The kit installation has to be carried out by qualified installers and it can only be used the components of the kit indicated in this ETA,
- the supervision of the amount of material used (kg/m²) and the control visual to check that each coat cover totally the one below, can ensure the minimum thickness of the kits,
- inspection of the roof surface (cleanliness and correct preparation) before applying the roof waterproofing,
- It is applied by projection device in heat, with the following characteristics: Pressure 150-200 bar, Deposit temperature product 80°C, temperature product conduct 75°C.

Before, the installation of MAXELASTIC POLY, it is recommended to read its security card.

⁽¹⁾ The technical documentation of this ETA is deposited at IETcc and, as far as relevant for the tasks of the approved bodies involved in the attestation of conformity procedure, is handed over to the approved bodies.

Use, maintenance and repair of the works. In those roofs with deteriorated areas of the waterproof layers, they will be repaired removing all the deteriorated layers. Afterwards, the new product will be assembled following the installation instruction and the new coats must overlap, at least 3 cm, to the coat no deteriorated. Further installation details are laid down in the MTD place at IETcc.

3 Performance of the product and references to the methods used for its assessment

The identification tests and the assessment for the intended use of this LARWK according to the Essential Requirements were carried out in compliance with the ETA Guidance n. 005: Guideline for European Technical Approval of Liquid applied roof waterproofing kits, ETAG 005, edition 2004, Part 1 "General" and Part 6 "Specific stipulations for kits based on polyurethane" (called ETAG 005, in this ETA).

3.1 LARWK Characteristics

Safety in case of fire ((BWR 2)

External fire performance. Classification: B_{roof}(t1) according EN 13501-5 for supports included in point 1 for roof slope < 20°, except for the extruded polystyrene support that the classification is NPD.

Reaction to fire. Euroclass F

Hygiene, health and environment (BWR 3)

Resistance to water vapour (EN 1931). $\mu = 2279$

Watertightness (EOTA TR-003). Watertight

Statement of dangerous substances. According to the manufacturer's declaration taking account of EOTA TR 034, the product installed does not contain and release any dangerous substance.

Resistance to wind loads (EOTA TR-4). Pass (>50 KPa)

Resistance to dynamic indentation (EOTA TR- 6). Resistance Level: I₄

Resistance to static indentation (EOTA TR-7).

Support	Load (N)	Resistance level
Steel	250	L4
Extruded polystyrene	250	L4

Resistance to fatigue movement (1000 cycles) (EOTA TR-8). Pass

Resistance to low temperatures effects (-20°C). Dynamic indentation, Resistance Level: I₄

Resistance to high temperatures effects. Static indentation

Temperature °C	Support	Load (N)	Resistance level
60°	Steel	250	L4
	Extruded polystyrene	250	L4
90°	Steel	250	L4
	Extruded polystyrene	250	L4

Resistance to heat ageing (EOTA TR-11). The samples are exposed to 80°C during 200 days.

Tests	Results
Fatigue movement	pass
Dynamic indentation (-20°C)	I ₄
Tensile strength (MPa) (EN ISO 527-3) (initial / ageing)	23 / 17
Tensile elongation (%) (EN ISO 527-3) (initial / ageing)	315 / 326

Resistance to UV-radiation in the presence of moisture (EOTA TR- 10). The samples are exposed 5.000 hours to UV-radiation.

Tests	Results
Dynamic indentation (-10°C)	I ₄
Tensile strength (MPa) (Type 2) (EN ISO 527-3) (initial / ageing)	23 / 17
Tensile elongation (%) (EN ISO 527-3) (initial / ageing)	315 / 372

Resistance to hot water ageing (EOTA TR-12).The samples are kept in touch with water at 60°C over 60 for load user of P3 and 180 days for P4.

Temperature °C	Support	60 D		180 D	
		Load (N)	Resistance Level	Load (N)	Resistance Level
60°	Steel	250	L4	250	L4
	XPS	250	L4	250	L4
90°	Steel	250	L4	250	L4
	XPS	250	L4	150	L2

Resistance to wind loads Pass (>50 KPa)

Resistance to plant roots (EN 13948). This kit is resistance to plants roofs.

Safety in use (BWR 4)

Slipperiness (ENV 12633:2003 Annex A). The kit with MAXURETHANE PRIMER +MAXELASTIC POLY +MAXURETHANE 2C+ BISEAL MEV (8%), show a Rd= 50.. According to EN 13893: NPD.

Related aspects of serviceability

Effect of weather conditions. The system does show changes in its tensile properties, when the system is assembled and cured under two temperature conditions of 5°C and 40°C, but these values obtained complied with the manufacturer's specifications (pass).

Effect of day joints. The delamination strength test performed on a layer assembled over other one, it shows a good delamination strength, being upper to required value of 50 KPa. (pass).

3.2 Characteristics of the components

The characteristics of the components of this System show the following values, which compliance with their respective tolerances stated in the Manufacture Technical Dossier (MTD).

MAXELASTIC POLY. Waterproofing liquid constituted by polieter-amines and pre-polymer of isocyanate, with loads and pigments mineral, and additives (anti-air entering, biocides, etc.). The main characteristics of this waterproof liquid are:

Properties	Component A	Component B
Density (g/cm ³) (ISO 1675)	1,11 ± 5%	1,09 ± 5%
Dry extract (105°C) (% weight) (EN 1768)	100	100
Ash content (450°C) (% weight) (EN 1879)	≤ 1	≤ 1
Viscosity (cps), (S63, 30 rpm, 25°C) (EN ISO 2555)	600 ± 50	650 ± 50

MAXURETHANE PRIMER

Properties	Component A	Component B
Density (g/cm ³) (ISO 1675)	1,19 ± 5%	1,03± 5%
Dry extract (105°C) (% weight) (EN 1768)	100	100
Ash content (450°C) (% weight) (EN 1879)	50 ± 5%	20 ± 5%
Viscosity (cps), (S63, 30 rpm, 25°C) (EN ISO 2555)	450 ± 50	900 ± 50

MAXURETHANE 2C. UV External protection. Aliphatic Polyurethane resins.

Properties	Component A	Component B
Density (g/cm ³) (ISO 1675)	1,34 ± 5%	1,34 ± 5%
Dry extract (105°C) (% weight) (EN 1768)	100	100
Ash content (450°C) (% weight) (EN 1879)	37 ± 3	≤ 1
Viscosity 20°C: Comp A (s), (Ford Cup n° 4) / Comp B (cps), (RV3, 10 rpm)	80 ± 10	600 ± 100

BISEAL MEV (8%)

Properties	Values
Nature	Polyamide
Form	Micronized particles
Weight (g/l)	± 640
Density (g/cm ³)	±1,22
Melting range (°C)	150 ~ 160
Particle size (µm)	150 ~ 280

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

System of Attestation of Conformity. The European Commission according to her decision (98/599/EC of October 1998, Official Journal of the European Communities N° L 287, 24.10.1998) on the procedure of attestation of conformity for the procedure of attestation of conformity (Annex III, clause 2(ii) second possibility of EU Regulation 305/2011) for liquid applied roof waterproofing kits has laid down for these Kits.

Product	Intended uses	Level or Classes	System
MAXELASTIC POLY	Liquid Applied Roof Waterproofing Kit	Any	3

According to this decision, system 3 of Attestation of Conformity also applies with regard to external fire performance. The system 3 provides: Tasks for the manufacturer: Factory production control and Tasks for the approved body: Initial type-testing of the product.

5 Technical details necessary for the implementation of the AVCP system, as provided for the applicable EAD

The ETA is issued for this kit on the basis of agreed data/information, deposited at IETcc, which identifies the product that has been assessed and judged. It is the manufacturer's responsibility to make sure that all those who use the kit are appropriately informed of specific conditions according to sections 1, 2, 4 and 5 including the annexes of this ETA. Changes to the ETICS or the components or their production process, which could result in this deposited data/information being incorrect should be notified to the IETcc before the changes are introduced. IETcc will decide whether or not such changes affect the ETA and if so whether further assessment or alterations to the ETA shall be necessary.

5.1 Tasks of the manufacturer

Factory production control. The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this ETA.

The manufacturer may only use components stated in the technical documentation of this ETA including Control Plan. The incoming raw materials are subjected to verifications by the manufacturer before acceptance.

The factory production control shall be in accordance with the Control Plan⁽²⁾ which is part of the Technical Documentation of this ETA. The Control Plan has been agreed between the manufacturer and the IETcc and is laid down in the context of the factory production control system operated by the manufacturer and deposited at the IETcc. The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan

(2) The control plan is a confidential part of this European Technical Assessment and only handed over to the notified body involved in the procedure of attestation of conformity.

Other tasks of the manufacturer. The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in section 4 in the field of LARWK in order to undertake the actions laid down in this clause. For this purpose, the control plan shall be handed over by the manufacturer to the notified bodies involved.

For initial type – testing, the results of the tests performed as part of the assessment for the ETA shall be used unless there are changes in the production line or plant. In such cases the necessary initial type- testing has to be agreed with the IETcc.

The manufacturer shall make a declaration of conformity, stating that the construction product is in conformity with the provisions of this ETA.

5.2 Tasks of notified bodies. The notified body shall perform

Initial type-testing of the product. The initial type-testing have been conducted by the IETcc to issued this ETA in accordance with chapter 5 of the guideline “Liquid applied roof waterproofing kits” (ETAG 005) part 1 and 6. The verifications underlying this ETA have been furnished on samples from the current production; these will replace the initial type-testing carried out by the manufacturer. The IETcc has assessed the results of these tests in accordance with chapter 6 of this ETA –Guideline, as part of the ETA issuing procedure.

Issued in Madrid on 24 february 2015.

by

Instituto de Ciencias de la Construcción Eduardo Torroja

CONSEJO SUPERIOR DE INVESTIGACIONES CIENTÍFICAS

c/ Serrano Galvache 4. 28033 Madrid (Spain).

director.ietcc@csic.es www.ietcc.csic.es



On behalf of the Instituto de Ciencias de la Construcción Eduardo Torroja

Marta María Castellote
Director

Annex 1.

Characteristics of the System "MAXELASTIC POLY"

Minimum thickness	1,4 mm
Water vapour diffusion resistant factor	$\mu \approx 2279$
Resistance to wind loads	> 50 KPa
Resistance to plant roots	Resistant
Statement on dangerous substances	Does not contain any
Resistance to slipperiness	Rd = 50

Performance levels according to the intended use

External fire performance	Broof (t1) roof slope < 20°// NPD: XPS support
Fire reaction	F
Expected working life	W3
Climatic zone of use	S (Severa)
User loads	P4:TH2 // P3: TH4
Roofs slopes	S1 – S4
Minimum surface temperatures	TL3 (- 20 °C)
Maximum surface temperatures	TH4-TH2