

INSTITUTO DE CIENCIAS DE LA CONSTRUCCIÓN EDUARDO TORROJA

C/Serrano Galvache n. 4. 28033 Madrid (Spain)Tel.: (34) 91 302 04 40 / Fax: (34) 91 302 07 00direccion.ietcc@csic.eswww.ietcc.csic.es





European Technical Assessment

ETA 20/ 0160 of 04/ 04/ 2020

English translation prepared by IETcc. Original version in Spanish language

General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) N°305/2011:

Instituto de Ciencias de la Construcción Eduardo Torroja (IETcc)

Trade name of the construction product

Product family to which the construction product belongs

Manufacturer

Manufacturing plant(s)

This European Technical Assessment contains

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of

CINGARD® EP500

Liquid Applied Roof Waterproofing Kit, based on Pure Polyurea

CIN - Corporação Industrial do Norte, S.A. Av de Dom Mendo, 831 - 4474-009 Maia - Portugal

CIN - Corporação Industrial do Norte, S.A. Av de Dom Mendo, 831 - 4474-009 Maia - Portugal

8 pages including 1 Annex which form an integral part of this assessment.

Annex 2. Contain confidential information and is not included in the ETA when that assessment is publicly available

Guideline for European Technical Approval (ETAG) nº 005, part 1-6 ed. 2004, used as European Assessment Document (EAD)

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of the product

CINGARD® EP500 is a liquid applied roof waterproofing membrane (LARWK) based on a resin of Polyurea, manufactured by the company CIN, SA. It consists of a Polyurea resins, bi-component, elastomeric without internal protection layer; which once polymerised conforms a jointless elastic lining, in form of a layer completely bonded to the support (concrete, mortar, ceramic, wood, steel, metal alloys, bituminous & PVC membranes, polyurethane foam (PU) and extrude polyestyrene (XPS)) and with a final UV protective coat. This LARWK comprises the following components, which are factory produced by the manufacturer or a supplier.

Components	Trade name	Total Consumption	
	C-Floor® Primer E150 DP (for concrete) (epoxy)	≥ 0.50 kg/m ²	
	C-Pox® ST170 (for steel) (epoxy)	≥ 0.17 kg/m ²	
Primer ⁽¹⁾	C-Floor® PU310 SL (XPS, EPS, PU and PVC membranes, wood and	≥ 0.1 kg/m ²	
	mineral self-protected bituminous roofing sheets) (polyurethane)	≥ 0.1 kg/III	
	Cingard® Bond Primer (for LARWK on LARWK) (polyurethane)	0.05 – 0.1 kg/m ²	
Waterproofing membrane CINGARD® EP500		≥ 1.5 kg/m ²	
UV protection	UV protection C-Floor® PAS810 FD Flex (polyaspartic)		
Film Slipperiness	UV protection of this ETA + 5% of C-Floor® Anti-Slip Additive 850 + 10% C-Thane® R/T		

This kit shows the following working life:

Product	Working life	Minimum thickness (mm)
CINGARD® EP500	25	1.4

The LARWK "CINGARD® EP 500" is designed and installed in accordance with the manufacturer, design and installation instructions, deposited at the IETcc.

2 Specification of the intended use in accordance with the applicable EAD

The intended use of this System is the waterproofing of roof against the water, as in liquid as vapour form. This LARWK fulfils the Basic works requirements no 2 (Safety in case of fire), no 3 (Hygiene, health and the environment) and no 4 (Safety in use) of the European Regulation 305/11.

This LARWK is made of non load-bearing construction elements. It does not contribute directly to the stability of the roof on which is installed, but it can contribute its durability by providing enhanced protection from the effect of weathering.

This LARWK can be used on new or existing (retrofit) roofs. It can also be used on horizontal surfaces (singular details).

The performance levels of this System according to the ETAG 005 (part 1-6) are included in the annex 1. The provisions made in this European Technical Assessment (ETA) are based on an assumed intended working life of the system of 25 years (W3). The indication given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are only to be regarded as a means for choosing the right products in relation to the expected economically reasonable working life of the works. "Assumed intended working life" means that, when an assessment following the ETAG provisions is made, and when this working life has elapsed, the real working life may be, in normal use conditions, considerably longer without major degradation affecting the Basic works requirements.

Installation. The Kit is installed on site. It is the responsibility of the manufacturer to guarantee that the information about design and installation of this LARWK is effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this European Technical Assessment. Besides, all the data concerning the execution shall be clearly indicated on the packaging and/or the enclosed instruction sheets using one or several illustrations.

<u>Design.</u> The fitness of the respective use for the levels of performance of this System stated in Annex 1 complies with the Spanish national requirements. In the MTD the manufacture gives information on the quantities consumed and the processing, which shall lead to a thickness of the roof waterproofing \geq 1.4 mm.

⁽¹⁾ Depending on support condition other type of primers may be advisable according to the manufacturer.

Execution. Particularly, it is recommended to consider:

- The kit installation has to be carried out by qualified installers,
- it can only be used the components of the kit indicated in this ETA,
- the supervision of the amount of material used (kg/m²) and the control visual to check that each coat cover totally the one below, can ensure the minimum thickness of the kits,
- inspection of the roof surface (cleanliness and correct preparation) before applying the roof waterproofing,
- it is applied by a hot spray machines. Temperatures, component A: 65 70 °C; component B: 75 80 °C; Hoses: 70 80 °C. Pressure about 150 200 bars.

Before the installation of CINGARD® EP500, it is recommended to read its safety and technical data sheet, available in the manufactures website.

Use, maintenance and repair of the works. In those roofs with deteriorated areas of the waterproof layers, they will be repaired removing all the deteriorated layers. Afterwards, the new product will be assembled following the installation instruction and the new coats must overlap, at least 3 cm, to the coat no deteriorated. Further installation details are laid down in the MTD place at IETcc.

3 Performance of the product and references to the methods used for its assessment

The identification tests and the assessment for the intended use of this LARWK according to the Basic works requirements were carried out in compliance with the ETA Guidance n. 005: Guideline for European Technical Approval of Liquid applied roof waterproofing kits, ETAG 005, edition 2004, Part 1"General" and Part 6 "Specific stipulations for kits based on polyurethane" (called ETAG 005, in this ETA).

3.1 LARWK Characteristics Essentials

Safety in case of fire ((BWR 2)

External fire performance. Classification: B_{roof}(t1) according to EN 13501-5, for concrete, steel and other metal surfaces and ceramic supports.

Reaction to fire. Classification: E/E_{fl} (EN 13501-1) for non combustible substrates.

Hygiene, health and environment (BWR 3)

Statement of dangerous substances. According to the manufacturer's declaration taking account of EOTA TR 034, the product installed does not contain and release any dangerous substance.

Resistance to water vapour (EN 1931). $\mu > 1400$

Samples	Thickness (mm)	g/(m²/d)	μ
CINGARD® EP500	2	14	1500

Watertightness (EOTA TR-003). Watertight

Resistance to wind loads (EOTA TR-004). Pass (> 50 kPa)

Resistance to mechanical damage

Resistance to dynamic indentation (EOTA TR-006). Resistance Level: 14

Resistance to static indentation (EOTA TR-007). Resistance Level: L4

Resistance to fatigue movement (1000 cycles) (EOTA TR-008). Pass

Resistance to the effects of low and high surface temperatures

Resistance to low temperatures effects (-20 °C). Dynamic indentation. Resistance Level: I4

Resistance to high temperatures effects (90 °C). Static indentation. Resistance Level: L4

Resistance to ageing media (heat and water)

Resistance to heat ageing (EOTA TR-011). The samples are exposed to 80 °C during 200 days.

Tests	CINGARD® EP500
Fatigue movement	Apt
Dynamic indentation (-20°C)	14
Tensile strength (MPa) (EN-ISO 527-3) (initial/ ageing)	21 / 22
Tensile elongation (%) (EN-ISO 527-3) (initial/ ageing)	766 / 727

Resistance to hot water ageing (EOTA TR-012). The samples are kept in touch with water at 60 °C over 60 and 180 days and the following tests were performed: The delamination strength (kPa) (Concrete): Apt (> 50 kPa) and Static indentation a 90°C with a level of resistance L4 in any support.

Resistance to UV-radiation in the presence of moisture (EOTA TR-010). The samples are exposed 5000 hours to UV-radiation with one topcoat.

Tests	CINGARD® EP500 + C-Floor® PAS810 FD Flex
Dynamic indentation (-10 °C)	14
Tensile strength (MPa) (EN-ISO 527-3) (initial/ ageing)	20 / 15
Tensile elongation (%) (EN-ISO 527-3) (initial/ ageing)	736 / 534

Resistance to plant roots (EN 13948). NPA

Related aspects of serviceability

Effect of weather conditions. The system shows a slight change in its tensile properties and none in the dynamic indentation resistance, when the system is assembled and cured under two temperature conditions of 5 °C and 40 °C (pass).

Effect of day joints. The delamination strength test performed on a layer assembled over other one, it shows a good delamination strength, being upper to required value of 50 kPa (pass).

Safety in use (BWR 4)

Slipperiness (ENV 13893). NPA. The test was performed according to EN 13036-4.

Film Slipperiness	Results
C-Floor® PAS810 FD Flex + 5% of C-Floor® Anti-Slip Additive 850 + 10% C-Thane® R/T	PTV = 56

3.2 Characteristics of the components

The characteristics of the components of this System show the following values, which compliance with their respective tolerances stated in the Manufacture Technical Dossier (MTD).

PRIMERS

		C-Floor® Prim	er E150 DP	C-Floor® Pl	J310 SL	
Properties	Standard	Standard Components				
		Α	В	Α	В	
Density (g/cm³) (23 °C)	EN ISO 2811-1	1.110 - 1.170	0.979 - 1.019	1.189 - 1.249	1.200 - 1.260	
Dry Extract (1h at 105 °C) (% weight)	EN ISO 3251	100	100	94.8 - 96.8	100	
Ash content (450 °C) (% weight)	EN ISO 3451-1	0	0	23.2 - 25.2	0	
Viscosity (cps) (23 °C)	ISO 2555	500 - 700	1300 - 2300	3200 - 5200	70 - 110	

		Cingard® E	Sond Primer		C-Pox® ST170	
Properties	Standard	Component				
		Α	В	A (0505)	A (0507)	В
Density (g/cm³) (23 °C)	EN ISO 2811-1	1.130 - 1.190	0.845 - 0.885	1.350 - 1.400	1.433 - 1.473	1.350 - 1.390
Dry Extract (1h at 105 °C)* Dry Extract (20min at 140 °C)** (% weight)	EN ISO 3251	69.0 - 71.0	0	96.6 - 98.6	96.0 - 98.0	77.1 - 79.1
Ash content (450 °C) (% weight)	EN ISO 3451-1	0	0	29.4 - 31.4	33.2 - 34.2	47.8 - 49.8
Viscosity (cps) (23 °C)	ISO 2555	300 - 500	Not measurable	2200 - 3400	9600 - 11600	10200 - 13200

^{*} Cingard Bond Primer ; ** C-Pox® ST170

CINGARD® EP500. Constituted by polyamines and isocyanates. Containing also a small quantity of pigments and additives. The main characteristics of this waterproof liquid are:

Properties	Standard	Component A	Component B
Density (g/cm³) (23 °C)	EN ISO 2811-1	1.035 - 1.095	1.095 - 1.115
Dry extract (1h at 105°C) (% weight)	EN ISO 3251	> 99.0	100
Ash content (450°C) (% weight)	EN ISO 3451-1	7.8 - 8.6	0
Viscosity (cps) (23 °C)	ISO 2555	450 - 650	640 - 890

External UV protection. Two-component polyaspartic resin. It may be coloured in different RAL colours.

		C-Floor [®] PAS810 FD Flex Components		
Properties	Standard			
	A		В	
Density (g/cm³) (23 °C)	EN ISO 2811-1	1.302 - 1.382	1.116 - 1.176	
Dry extract (1h at 105°C) (% weight)	EN ISO 3251	86.0 - 88.0	> 99.0	
Ash content (450°C) (% weight)	EN ISO 3451-1	28.8 - 30.8	0	
Viscosity (cps) (23 °C)	ISO 2555	800 - 1200	800 - 1200	

Film Slipperiness. The topcoat finish is made with the external UV protection with a 5 % in weight of C-Floor Anti-Slip Additive 850 and 10 % of C-Thane R/T

Properties	C-Floor® Anti-Slip Additive 850	C-Thane® R/T
Nature	Polypropylene	Hydrocarbon based thinner
Form	Micronized particles	Liquid
Density (g/cm³)	0.880 - 0.920	0.845 - 0.890
Melting range (°C)	166 - 168	Not applicable
Particle size	845 - 890 μm	Not applicable

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

System of Attestation of Conformity. The European Commission according to her decision (98/599/EC of October 1998, Official Journal of the European Communities N° L 287, 24.10.1998) on the procedure of attestation of conformity for the procedure of attestation of conformity (Annex III, clause 2(ii) second possibility of EU Regulation 305/2011) for liquid applied roof waterproofing kits has laid down for this type of material.

Product	Intended uses	Level or Classes	System
CINGARD® EP500	Liquid Applied Roof Waterproofing Kit	Any	3

According to this decision, system 3 of Attestation of Conformity also applies with regard to external fire performance. The system 3 provides: Tasks for the manufacturer: Factory production control and Tasks for the notified body: Initial type-testing of the product.

5 Technical details necessary for the implementation of the AVCP system, as provided for the applicable EAD

The ETA is issued for this kit on the basis of agreed data/information, deposited at IETcc, which identifies the product that has been assessed and judged. It is the manufacturer's responsibility to make sure that all those who use the kit are appropriately informed of specific conditions according to sections 1, 2, 4 and 5 including the annexes of this ETA. Changes to kit, the components or their production process, which could result in this deposited data/information being incorrect, should be notified to the IETcc before the changes are introduced. IETcc will decide whether or not such changes affect the ETA and if so whether further assessment or alterations to the ETA shall be necessary.

5.1 Tasks of the manufacturer

Factory production control. The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this ETA.

The manufacturer may only use components stated in the technical documentation of this ETA including Control Plan. The incoming raw material is subjected to verifications by the manufacturer before acceptance.

The factory production control shall be in accordance with the Control Plan⁽²⁾ which is part of the Technical Documentation of this ETA. The Control Plan has been agreed between the manufacturer and the IETcc and is laid down in the context of the factory production control system operated by the manufacturer and deposited at the IETcc. The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

Other tasks of the manufacturer. The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in section 4 in the field of LARWK in order to undertake the actions laid down in this clause. For this purpose, the control plan shall be handed over by the manufacturer to the notified bodies involved.

For initial type – testing, the results of the tests performed, as part of the assessment for the ETA shall be used unless there are changes in the production line or plant. In such cases the necessary initial type- testing has to be agreed with the IETcc.

The manufacturer shall make a declaration of conformity, stating that the construction product is in conformity with the provisions of this ETA.

5.2 Tasks of notified bodies. The notified body shall perform

Initial type-testing of the product. The initial type-testing have been conducted by the IETcc to issued this ETA in accordance with ETAG 005 (part 1-6) "Liquid applied roof waterproofing kits". The verifications underlying this ETA have been furnished on samples from the current production; these will replace the initial type-testing carried out by the manufacturer.

Issued in Madrid on 4 April 2020 by



Instituto de Ciencias de la Construcción Eduardo Torroja

CONSEJO SUPERIOR DE INVESTIGACIONES CIENTÍFICAS c/ Serrano Galvache 4. 28033 Madrid (Spain).

c/ Serrano Galvache 4. 28033 Madrid (Spain). director.ietcc@csic.es www.ietcc.csic.es







Director IETcc-CSIC

⁽²⁾ The control plan is a confidential part of this European Technical Assessment and only handed over to the notified body involved in the procedure of attestation of conformity..

Annex 1.

Characteristics of the System "CINGARD® EP 500"

Minimum thickness	1.4 mm
Water vapour diffusion resistant factor	$\mu = 1.500$
Resistance to wind loads	> 50 kPa
Resistance to plant roots	NPA
Statement on dangerous substances	Without dangerous substances
Resistance to slipperiness	PTV = 56

Performance levels according to the intended use

External fire performance	B _{roof} (t1) Non combustible substrates
Fire reaction	E / E _{fl}
Expected working life	W3
Climatic zone of use	S
User loads	P4: TH2 /// P3: TH4
Roofs slopes	S1 - S4
Minimum surface temperatures	TL3
Maximum surface temperatures	TH4